

Gehring Tricot Corp.

Batch Quality Analysis

Report Date: 13-Dec-12

Time: 11:06

Std Meas Geometry: %R LAV SCI UV 400

Batch Meas Geometry: %R LAV SCI UV 400


Standard:

P379 Rich Black AUB

Batch:

7231103 dye

Under Illuminant D65 10 Deg



Standard Name:
P379 Rich Black AUB

Batch Name:
7231103 dye

III/Obs	L*	a*	b*	C*	H*
D65 10 Deg	17.38	1.18	-2.90	3.13	292.10
D65 10 Deg	16.95	1.48	-3.46	3.77	293.18

CIE L*a*b* Color Difference

Batch Measured: 30-Nov-12 10:51:17

III/Obs	DL*	Da*	Db*	DC*	DH*	DE*
D65 10 Deg	-0.43	0.31	-0.57	0.64	0.06	0.77
F02 10 Deg	-0.52	0.12	-0.77	0.78	0.07	0.93
A 10 Deg	-0.42	0.40	-0.50	0.63	0.12	0.77