



DIVERSIFIED

TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

333 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

January 3, 2013

Ms. Wei Chang
VERATEX, INC.
254 Fifth Avenue
New York, NY 10001

Reference: Laboratory Test Report
Lab Identification No. 4865
Invoice No. 35358 (Attached)

Dear Ms. Chang:

One (1) fabric sample, identified as **STYLE V406/7**, was received and tested in accordance with ASTM D 4964-96, "Tension and Elongation of Elastic Fabrics (Constant-Rate-of-Extension Type Tensile Testing Machine)". The results are as follows:

	TEST RESULTS (%)	
	Length	Width
Elongation @ 4.4 lbf	2.94	40.78
Elongation @ 6.6 lbf	3.40	47.49
Elongation @ 10 lbf	3.92	53.19
Elongation @ 15 lbf	4.53	58.26
Elongation @ 20 lbf	5.06	61.93

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment

OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.



DIVERSIFIED

TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

January 3, 2013

Ms. Wei Chang
VERATEX, INC.
254 Fifth Avenue
New York, NY 10001

Reference: Laboratory Test Report
Lab Identification No. 4865
Invoice No. 35558 (Attached)

Dear Ms. Chang:

One (1) fabric sample, identified as STYLE V406/7, was received and tested in accordance with ASTM D 2594-2004, "Standard Test Methods for Stretch Properties of Knitted Fabrics Having Low Power". Per your request, the test was modified by using 15 and 20 lbs. The results are as follows:

<u>Test Procedure</u>	<u>Test Results</u>	
	<u>Length</u>	<u>Width</u>
% Stretch at 15 lbs.	7.0	63.0
% Stretch at 20 lbs.	10.0	69.0


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment

QUALITY TESTS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.



DIVERSIFIED

TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

"We Test Per Your Request"

January 3, 2013

Ms. Wei Chang
VERATEX, INC.
254 Fifth Avenue
New York, NY 10001

Reference: Laboratory Test Report
Lab Identification No. 4865
Invoice No. 35558 (Attached)

Dear Ms. Chang:

One (1) fabric sample, identified as STYLE V406/7, was received and tested in accordance with ASTM D 3786-09, "Hydraulic Bursting Strength of Knitted Goods and Nonwoven Fabrics: Diaphragm Bursting Strength Tester Method". The results are as follows:

	Test Results (lbs./sq.in.)
1	127
2	122
3	121
4	129
5	131
Avg.	126

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

REP/mr
Attachment

OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. OUR LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING OR IN THE GENERAL PUBLIC.