



VERATEX INCORPORATED 160 MADISON AVENUE, NEW YORK, NY 10016 (212) 683-9300 FAX (212) 889-5573

March 9, 2009

Tommy Bridges  
Harodite Industries, Inc.  
2 Henderson Court  
Travelers Rest, SC 29690

RE: V10836 Polyester Knit

Via: Fax

Dear Tommy:

We have completed development of the Veratex product V10836 and we are pleased to inform you that the finished fabric passed all the required tests and meets the specifications outlined in NCTR/F PD 3-00A.

Following is a summary of the test result from Diversified Testing Laboratories, Inc., an independent certified testing lab in Burlington, North Carolina.:

Test		Standard	V10836
ASTM D3787	Bursting Strength	80	112.4
AATCC-135(3)Vaiii	Dimensional Stability	2% Wale 2% Course	1% 2%
AATCC 61 Test 3A	Laundering (3 cycles)	>=4	5
AATCC 15	Perspiration	>=4	5
AATCC 132	Dry Cleaning	>=4	5
AATCC81	pH	5.0-8.5	6.9

In addition, the fabric was tested at our own physical testing laboratory as follows:

Test		Standard	V10836
Punched Weight		>=2.2 oz/sq	2.24 oz/sq
Construction		38 Wales 52 Courses	38 Wales 62 Courses
Fiber		100% Polyester	100% Polyester

Attached are the actual test results from Diversified.

We look forward to hearing from you.

Sincerely,

Claude Simon