



**DIVERSIFIED  
TESTING LABORATORIES, INC.**

"We Test Per Your Request"

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
[www.diversifiedtestinglabs.com](http://www.diversifiedtestinglabs.com)

March 9, 2009

Mr. Claude Simon  
FAIRLANE, DIVISION OF VRTX  
1204 Springwood Avenue  
Gibsonville, NC 27249

Reference: Laboratory Test Report  
Lab Identification No. 9170  
Invoice No. 21580 (Attached)

Dear Mr. Simon:

One (1) fabric sample, identified as V10836 POLYESTER 60" WHITE, DYE ORDER 18081, was received and tested in accordance with AATCC Test Method 135-2004, "Dimensional Changes in Automatic Home Laundering of Woven and Knit Fabrics". The conditions used were: Machine Cycle: (3) Permanent Press; Wash Temperature: (V) 140F; Drying Procedure: (A) Tumble, (iii) Permanent Press. The test results are as follows:

% Dimensional Change			
1st Cycle		5 <sup>th</sup> Cycle	
Warp	Fill	Warp	Fill
1.7%	0.5%	2.0%	1.0%

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Karon S. Atkins

KSM/mr  
Attachment