

?

Veratex Inc., P.O. Box 682, New York, NY 10108  
Phone: 212 683 9300 Email: operations@veratex.nyc Fax: 212 889 5573

D Y E   O R D E R

DYE ORDER: 20297      DATE: 11/18/2024

TO: REBTEX, INC.  
40 INDUSTRIAL PARKWAY  
SOMERVILLE, NJ 08876

FINISHED STYLE: V10836      COLOR: WHITE      COLOR NO: 29153

FRAME: 3X49" OVERALL

REQUESTED GREIGE YIELD: 4.8 LIN      REQUESTED FINISHED WEIGHT: 2.2 OZ/SQ YD

FINISH: SOFT AS LOT 51167

COURSES PER INCH: 59      WALES PER INCH: 37

PUT UP: 300 YDS 2"OPEN

SUBMIT LAB DIP (Y/N): N      SUBMIT HEAD END (Y/N): Y

TO:  
CLAUDE SIMON  
71 TONJES ROAD  
CALICOON, NY 12723

GREIGE STYLE: V10640      KNTTER: SHAM      DATE GREIGE SHIPPED: / /

YARN DESCRIPTION: 20 /12 SD BW POLY M 1340  
40 /24 SD POLY MW06361

STYLE	CASE	PIECE	LBS	STYLE	CASE	PIECE	LBS
V10640		B06-9869	518.00	V10640		B06-9870	498.00
V10640		B06-9871	500.00	V10640		B06-9872	494.00
V10640		B06-9873	492.00	V10640		B06-9874	495.00
V10640		B06-9875	498.00	V10640		B06-9876	496.00
V10640		LPB06-9877	195.00				

TOTAL GREIGE LBS: 4186.00

SPECIAL INSTRUCTIONS-----

1. Watch finished weight. Must be 2.2 oz/sq minimum.
2. Add anti-stat finish.
3. Goods must be scoured and heat set.
4. Home washable and dryable.
5. CPI and WPI may vary. Must be 2.2 oz/sq minimum.
6. Watch pH level. Must be between 5.0 and 8.5.
7. Inspect goods for dirt, oil spots and ends out.
8. \*\*\*WATCH WRINKLING\*\*\* NO WRINKLES.
9. Double bag for shipping.

END