

Suggested Care of Textile Products by Fiber Group

Fiber Group	Cleaning Method	Safe to use		Dryer Temperature	Iron Temperature	Special Storage Consideration
		Water Temperature	Chlorine Bleach			
Acetate	Dry clean*	Warm 110-115°F	Yes	Low	Very low	Avoid contact with polish remover
Acrylic	Launder	Warm	Yes	Warm	Medium	—
Cotton	Launder	Hot (120-140°F)	Yes	Hot	High	Store dry to prevent
Polyester	Launder	Hot	Yes	Warm	Medium	—
Cotton L/P						
Flax	Launder	Hot	Yes	Hot	High	For longest wear, do not press in sharp creases. Prevent fiber breakage during as flat as possible.
Glass	Hand wash only	Hot	Yes	Line dry	Do not iron	—
Modacrylic	Launder	Warm	Yes	Low	Very low	—
Nylon	Launder	Hot	Yes	Warm	Low	—
Olefin	Launder	Warm	Yes	Warm	Very low	—
Polyester	Launder	Hot	Yes	Warm	Low	—
Rayon	Launder	Hot	Yes	Hot	High	Store dry to prevent
Rayon HWM	Launder	Hot	Yes	Hot	High	Store dry to prevent
Silk	Dry clean*	Warm	No	Warm	Medium	—
Spandex	Launder	Warm	No	Warm	Very low	—
Triacetate	Launder	Warm	Yes	Warm	Medium	—
Wool	Dry clean*	Warm	No	Warm	Medium, with steam	Protect from moths; store in plastic bag

* Or hand wash avoiding excessive agitation and stretching