



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

November 7, 2023

Mr. Claude Simon
VERATEX, INC.
P.O. Box 682
New York, NY 10108

Reference: Laboratory Test Report
Lab Identification No. 57326
Invoice No. 88634

Dear Mr. Simon:

One (1) fabric sample, identified as **Style: V10212; Lot#: 20007/7920602**, was received and tested in accordance with ASTM D 6413-15, “Standard Test Method for Flame Resistance of Textiles (Vertical Test)”. The results are as follows:

Test Results

Specimen Number	After Flame (seconds)		After Glow (seconds)		Char Length (inches)	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	6.5	0.0	0.0	0.0	5.3	5.3
2	8.8	0.0	0.0	0.0	5.7	5.8
3	8.1	0.0	0.0	0.0	4.8	6.0
4	0.0	0.0	0.0	0.0	5.1	5.2
5	<u>4.1</u>	<u>0.0</u>	<u>0.0</u>	<u>0.0</u>	<u>4.8</u>	<u>5.1</u>
Avg	5.5	0.0	0.0	0.0	5.1	5.5

Note: There were no occurrences of melting or drippings.

Sincerely,

Brian S. Dement

BSD/mr

